

Amendments to the Specification:

Please add the following new paragraph after paragraph [0045]:

[0045.1] Preferably, according to one embodiment of the present invention, a composition of this invention has from 65 to 99.9 weight % of monomer such as cyanoacrylate or blend of cyanoacrylates and is promoted to polymerize by 0.005 to 10 weight % of an initiator or accelerator.